

Description, Origin & Production



- **CUPA 3** is a blue black slate with a very rough surface which contains non rusting metallic particles. This slate is split to a thickness of 3.5 mm and 7-8 mm for the "Heavy" variant.
- San Pedro Quarry. San Pedro de Trones (Leon) Spain. Operating since 1892.
- 20,000 Tons/year.

Formats & Sizes



Formats Rectangular

Sizes (cm) Between 25x15 & 50x25, according to formats.

- UK : (Heavy) 30x20, 35x20, 40x20, 40x25, 50x25.
- Ireland : (Heavy) 50x25.
- France : 25x15, 27x18, 30x18, 30x20, 32x22, 33x23.
- Benelux : 25x15, 27x18, 30x20, 32x22.

* If you are interested in other formats please contact our Customer Service department.

Heavy 3

A unique slate, known as Heavy 3, is produced in the Cupa 3 quarry and is specially produced for the Scottish market as an alternative to Ballachulish slate. Heavy 3 is also ideally suited to Ireland's landscape and Atlantic climate. For more information about this product, please visit www.cupaheavy3.com

CUPA 3



Technical Specifications

CUPA 3 slates are in compliance with the following specifications:

- European Norm: EN 12326
- British Standard: BS 680: Part 2
- French Specifications: NF 228-02/01/01
- Belgium Specifications: ATG/H571

| | |
|--------------------------------------|--------------------|
| WATER ABSORPTION | 0.21% |
| CONTENTS OF CARBONATE NON CARBONATED | 0.43% |
| MoR CHARACTERISTIC | 57 |
| CARBONATES CONTENT | 0.40% |
| THICKNESS | 3.5mm, 5mm & 7-8mm |

Grading

All natural slate should be graded into at least 3 thicknesses prior to being placed on the roof. To minimize the effect of any variation in shade, slate should be drawn from at least 2 pallets at time.

As with any natural product, slate is subject to variance, and any slates that are identified at the time of grading as problematic should be cut and used at the eaves or ridge of the roof.

For further information on fixing natural slate please contact your supplier or visit www.cupanaturalslate.co.uk

The images shown may not correspond exactly to the product referenced.



www.cupanaturalslate.co.uk
www.cupaheavy3.com

UK: 45 Moray Place | EDINBURGH EH3 6BQ | Tel. +44 131 22 53 111 | Fax +44 131 22 05 463
 Spain: La Medua S/N | SOBRADELO DE VALDEORRAS | Ourense | Tel. +34 988 335 410 | Fax +34 988 335 599