

## Description, Origin & Production



- **CUPA 17** is a grey slate incrustated with non-rusting metal particles. Split to an average thickness of 3.4-7.6 mm.
- Trevinca Quarry. Paraje de Rozadais (Ourense), Spain. In operation since 1960.
- 8,000 Tons/year.

## Formats & Sizes



**Formats** Square & Rectangular.

**Sizes (cm)** Between 22x16 & 46x30, according to formats.

- UK: 40x25.

\* If you are interested in other formats please contact our Customer Service department.



# CUPA 17



## Technical Specifications

CUPA 17 slates are in compliance with the following specifications:

- European Specifications: EN 12326
- British Standard: BS 680: Part 2
- French Specifications: P32.301 & P32.302

WATER ABSORPTION	0.28%
CONTENTS OF CARBONATE NON CARBONATED	0.64%
MoR CHARACTERISTIC	47
CARBONATES CONTENT	0.50%
THICKNESS	3.5mm, 4.2mm & 7-8mm

### Grading

All natural slate should be graded into at least 3 thicknesses prior to being placed on the roof. To minimize the effect of any variation in shade, slate should be drawn from at least 2 pallets at time.

As with any natural product, slate is subject to variance, and any slates that are identified at the time of grading as problematic should be cut and used at the eaves or ridge of the roof.

For further information on fixing natural slate please contact your supplier or visit [www.cupanaturalslate.co.uk](http://www.cupanaturalslate.co.uk)

The images shown may not correspond exactly to the product referenced.



[www.cupanaturalslate.co.uk](http://www.cupanaturalslate.co.uk)

UK: 45 Moray Place | EDINBURGH EH3 6BQ | Tel. +44 131 22 53 111 | Fax +44 131 22 05 463

Spain: La Medua S/N | 32330 | SOBRADELO DE VALDEORRAS | Ourense | Tel. +34 988 335 410 | Fax +34 988 335 599