

## CUPA 4





- · CUPA 4 is a blue black slate with a smooth surface. Split to an average thickness of 3.5 and 5mm and 8mm for the "CUPA d'Art"
- · Armadilla Quarry. Benuza (Leon), Spain. In operation since 1968.
- · 30,000 Tons/year.

## Formats & Sizes





**Formats** 

Rectangular, Cut shoulders, Fish Scale & Rounded.

Sizes (cm)

Between 22x16 & 50x25, according to formats.

- UK: 50x25.
- France: From 22x16 to 40x25. CUPA d'Art in format 30x20 & 32x22 (4,5 mm 8 mm).

  Benelux: 25x15, 25x18, 27x15, 27x18, 30x20, 32x22, 35x20, 35x22, 35x25, 40x20, 40x22, 40x25.
- Spain: From 22x16 to 40x25.
- \* If you are interested in other formats please contact our Customer Service department.



## Technical **Specifications**

CUPA 4 slates are in compliance with the following specifications:

- European Specifications: EN 12326
- · British Standard: BS 680: Part 2
- French Specifications: NF 228-02/02/01
- Belgian Specifications: ATG/H517

WATER ABSORPTION	0.27%
CONTENTS OF CARBONATE NON CARBONATED	0.44%
MoR CHARACTERISTIC	64
CARBONATES CONTENT	0.60%
THICKNESS	3.5mm to 5mm & 7-8mm

## **Grading**

All natural slate should be graded into at least 3 thicknesses prior to being placed on the roof. To minimize the effect of any variation in shade, slate should be drawn from at least 2 pallets at time.

As with any natural product, slate is subject to variance, and any slates that are identified at the time of grading as problematic should be cut and used at the eaves or ridge of the roof.

For further information on fixing natural slate please contact your supplier or visit www.cupanaturalslate.co.uk

















