

Description, Origin & Production



- **CUPA 7** is a blue black slate with a smooth surface. Split to an average thickness of 3.5mm, 5mm and 7 to 8mm for the Heavy variant.
- Las Arcas Quarry. San Pedro (Leon), Spain. In operation since 1983.
- 22,000 Tons/year.

Formats & Sizes



Formats Rectangular & Rounded.

Sizes (cm) Between 25x15 to 50x25, according to formats.

- UK: 50x25. Heavy 30x20, 35x20, 40x20, 40x25 & 50x25.
- France: 25x18, 27x18, 30x18, 30x20, 30x22, 32x22, 35x20, 35x25, 40x20, 40x25 & 50x25.
- Benelux: 25x15, 25x18, 27x15, 27x18, 30x20, 32x22, 35x20, 35x25, 40x20, 40x22 & 40x25.
- Spain: 30x20, 32x22, 40x20 & 40x22

* If you are interested in other formats please contact our Customer Service department.





Technical Specifications

CUPA 7 slates are in compliance with the following specifications:

- European Specifications: EN 12326
- British Standard: BS 680: Part 2
- French Specifications: NF 228-02/06/01
- Belgian Specifications: ATG/H518

WATER ABSORPTION	0.27%
CONTENTS OF CARBONATE NON CARBONATED	0.38%
MoR CHARACTERISTIC	65
CARBONATES CONTENT	0.50%
THICKNESS	3.75mm to 5mm & 7-8mm

Grading

All natural slate should be graded into at least 3 thicknesses prior to being placed on the roof. To minimize the effect of any variation in shade, slate should be drawn from at least 2 pallets at time.

As with any natural product, slate is subject to variance, and any slates that are identified at the time of grading as problematic should be cut and used at the eaves or ridge of the roof.

For further information on fixing natural slate please contact your supplier or visit www.cupanaturalslate.co.uk

The images shown may not correspond exactly to the product referenced.



www.cupanaturalslate.co.uk

UK: 45 Moray Place | EDINBURGH EH3 6BQ | Tel. +44 131 22 53 111 | Fax +44 131 22 05 463

Spain: La Medua S/N | 32330 | SOBRADELO DE VALDEORRAS | Ourense | Tel. +34 988 335 410 | Fax +34 988 335 599